

**TECHNO ADHESIVES COMPANY**

12113 Mosteller Road  
Cincinnati, Ohio 45241

Phone: (513) 771-1584  
1-800-432-0107

Fax: (513) 771-1684  
[www.technoadhesives.com](http://www.technoadhesives.com)

**TECHNO ADHESIVE NO. 106**

**EASY SPRAY INSULATION ADHESIVE**

<b>BASE:</b>	Resin Modified Rubber
<b>VISCOSITY:</b>	Medium Thin Liquid (Brookfield 1000 - 3000 cps.)
<b>SPECIFIC GRAVITY:</b>	6.5 ± .2 Lbs./Gal.
<b>SOLVENT:</b>	Aliphatic Hydrocarbon
<b>SOLIDS:</b>	% by Weight 30% ± 2%
<b>COLOR:</b>	Clear, Green, Black or Red
<b>DESCRIPTION:</b>	A quick tack, easily sprayable adhesive, specifically designed for bonding insulation (fiberglass, expanded polystyrene, rubber foam, cork, felt and other light weight materials) to metal ducts and other construction surfaces.
<b>FIRE RESISTANCE:</b>	This adhesive has been approved under ASTM E84-67 as required by UL 465, UL 727, UL 723, MBFU 90A, NFPA 255, and UBC 42-1.
<b>BONDING TIME:</b>	15 seconds to 30 minutes single surface application, For greatly increased open times, apply to both surfaces and use as a contact bond cement. (recommended for expanded poly styrene)
<b>COVERAGE:</b>	Up to 600 Sq.Ft./Gal. When Sprayed, Less with Brush or Roller
<b>TEMPERATURE RANGE:</b>	-30°F to 200°F
<b>WATER &amp; MOISTURE RESISTANCE:</b>	Excellent
<b>CLEAN UP:</b>	Mineral Spirits or Petroleum Naptha
<b>CAUTION:</b>	This cement is flammable. Keep away from sparks and open flames. Provide adequate ventilation.

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy thereof is not guaranteed, it being specifically understood that there are no warranties either expressed or implied incident to the sale of this product. No person is authorized or empowered to make any statement or recommendation concerning said product not contained herein, and any such statement or recommendation so made shall not bind the company. Users assume all risk and liability whatsoever resulting from the use of this product and must confirm the adaptability thereof by their own tests.