

TECHNO ADHESIVES COMPANY

12113 Mosteller Road
Cincinnati, Ohio 45241

Phone: (513) 771-1584
1-800-432-0107

Fax: (513) 771-1684
www.technoadhesives.com

TECHNO ADHESIVE #259

EASY SPRAY FLEXIBLE FOAM ADHESIVE
NON-FLAMMABLE

BASE:	Synthetic Elastomer
SOLVENT:	Blend
COLOR:	Clear, Red or Green
CONSISTANCY:	Medium Thin Liquid, Brookfield 2/20 = 450 ± 50 CPS
SOLIDS:	By Wt. = 35 ± 1% by Volume = 40 ± 1%
SPECIFIC GRAVITY:	9.8 ± .2 LBS./GAL.

DESCRIPTION: This is a spray applied adhesive used for bonding all types of rubber and urethane flexible foams to themselves or to other materials such as cloth, wood, or metal. Techno Adhesive #259 may be used for one side application in certain bonding operations, where #159 will not perform. It has excellent application and working characteristics with very high coverage. Techno Adhesive #259 performs well in all areas of foam laminating and fabrication with minimal web formation under normal usage. It produces soft, non-dimpling bonds which will not harden or darken with age. Fabrics in contact with this bond line will not become stained after aging for long periods even when exposed to sunlight.

APPLICATION: Spray Atomization Pressure: 15 – 30 PSI
Fluid Pressure: 5 – 10 PSI
Binks 66SS Fluid Nozzle: 66SS Air Cap or Equal

COVERAGE: 400 – 600 Sq.Ft./Gal.

CAUTION: Avoid prolonged breathing of vapors and excessive contact with skin; use with adequate ventilation.

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy thereof is not guaranteed, it being specifically understood that there are no warranties either expressed or implied incident to the sale of this product. No person is authorized or empowered to make any statement or recommendation concerning said product not contained herein, and any such statement or recommendation so made shall not bind the company. Users assume all risk and liability whatsoever resulting from the use of this product and must confirm the adaptability thereof by their own tests.